

J-FOAM 55 EVA

A moderately firm, heat moldable EVA. A 50-55 duro EVA.
A firm EVA used for the base, posting or wedging.

Heating: 300°F for 1 to 2 minutes.

