

J-FOAM 65 EVA

A firmer heat moldable EVA. A 60-65 duro EVA. A firmer EVA used for rear foot post.

Heating: 300°F for 1 to 2 minutes.

